



VOC-free, no-clean soldering flux for selective soldering

Description:

SelectIF 2040 is a VOC-free and no-clean soldering flux developed for selective soldering.

The flux combines a wide process window in selective soldering with low residue formation.

SelectIF 2040 is suitable for soldering units with high thermal mass and hence high temperatures and long process times.

Due to its special composition, it leaves less residues after soldering than the conventional fluxes for selective soldering.

SelectIF 2040 tends to give low solder balling after soldering.

The flux is compatible with lead-free and SnPb alloys.

Additionally, the flux is absolutely halogen free, guaranteeing a high reliability after soldering.



Products pictured may differ from the product delivered

Physical and chemical properties:

Density at 20°C	: 1,00 g/ml ± 0,01
Colour	: clear
Odour	: sweet
Solid content (activity)	: 6,5 % ± 0,2
Halide content	: 0,00 %
Flash point (T.C.C)	: n.a.
Total Acid Number	: 44 mg KOH/g ± 2
IPC/ EN	: OR/ LO

Applying the flux

In selective soldering, the flux is usually being applied by a micro-jet nozzle. The correct amount of flux will depend on parameters like type of surface finishing, oxidation level, thermal mass of the board and component,...and soldering parameters like used alloy, soldering temperature and time, turbulence of the wave,...

It should be the goal to apply as little as possible flux with good soldering results. In practice this optimal flux volume is being determined by trial and error or by copying values of similar boards/solder joints. Compared to most fluxes, SelectIF 2040 typically only needs about half of the flux volume.



Key properties

- Wide process window
- Suitable for high temperatures and long process times
- Low residue
- Low tendency towards solder balling
- Compatible with SnPb and lead-free alloys
- Absolutely halogen free



Preheating and wave contact

In general a preheating is used to limit the temperature shock and to evaporate the solvent of the flux. It is advisable to have the water content evaporated before wave contact. A good preheating can promote through hole wetting. SelectIF 2040 has no lower limit for the preheating temperature. It is advisable to keep the preheating below 160°C when possible.

In selective soldering the wave contact is mostly determined by good through hole wetting. This is influenced by the preheating, the thermal mass of PCB and component, the wettability of the finishes, the solidification point of the used alloy and the working temperature. Like the flux amount, in practice this is being determined by trial and error or by copying values of similar boards/solder joints.

Typical contact times are between 1s and 3s but higher contact times are possible.

Test results

conform EN 61190-1-1(2002) and IPC J-STD-004A/B

Property	Result	Method
Chemical		
Flux designator	OR L0	J-STD-004A
Qualitative copper mirror	pass	J-STD-004A IPC-TM-650 2.3.32
Qualitative halide		
Silver chromate (Cl, Br)	pass	J-STD-004A IPC-TM-650 2.3.33
Quantitative halide	0,00%	J-STD-004A IPC-TM-650 2.3.35
Environmental		
SIR test	pass	J-STD-004B IPC-TM-650 2.6.3.7
Qualitative corrosion, flux	pass	J-STD-004A IPC-TM-650 2.6.15
Corrosion test	pass	Test Bono

Safety

SelectIF 2040 is non hazardous. Please consult the safety datasheet for more information.



Packaging

SelectIF 2040 is available in the following packages:

1L bottles

10L polyethylene drums

25L polyethylene drums

Trade name : SelectIF 2040 VOC-Free, No-Clean Selective Soldering Flux

Disclaimer

Because Interflux® Electronics N.V. cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our products should make their own test to determine the suitability of each such product for their particular purposes. The product discussed is sold without such warranty, either express or implied.

Copyright:

INTERFLUX® ELECTRONICS N.V.

www.interflux.com